

685271

PRO0008b 12/11/91  
Section 29 (1)  
Regulation 3.1 (2)

AUSTRALIA

Patents Act 1990

**NOTICE OF ENTITLEMENT**  
(To be filed before acceptance)


We, BASF AKTIENGESELLSCHAFT of, D-67056 LUDWIGSHAFEN, Federal Republic of Germany, being the applicant in respect of Application No.23442/95 state the following:

The Person nominated for the grant of the patent has entitlement from the actual inventors by virtue of employment of the inventors.

The person nominated for the grant of the patent is the applicant of the applications listed in the declaration under Article 8 of the PCT.

The basic applications listed in the declaration made under Article 8 of the PCT are the first applications made in a Convention country in respect of the invention.

By our Patent Attorneys,  
**WATERMARK PATENT & TRADEMARK ATTORNEYS**

  
.....  
**Shahnaz Irani**

**Registered Patent Attorney**

23 September, 1997

.....  
(Date)



AU9523442

(12) PATENT ABRIDGMENT (11) Document No. AU-B-23442/95  
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 685271

(54) Title  
INHERENTLY LIGHT- AND HEAT-STABILIZED POLYAMIDES

International Patent Classification(s)  
(51)<sup>6</sup> C08K 005/3435 C08G 069/48

(21) Application No. : 23442/95

(22) Application Date : 12.04.95

(87) PCT Publication Number : WO95/28443

(30) Priority Data

(31) Number	(32) Date	(33) Country
4413177	15.04.94	DE GERMANY
4429089	17.08.94	DE GERMANY

(43) Publication Date : 10.11.95

(44) Publication Date of Accepted Application : 15.01.98


(71) Applicant(s)  
BASF AKTIENGESELLSCHAFT

(72) Inventor(s)  
KLAUS WEINERTH; KARLHEINZ MELL; PAUL MATTHIES; LUDWIG BEER

(74) Attorney or Agent  
WATERMARK PATENT & TRADEMARK ATTORNEYS, Locked Bag 5, HAWTHORN VIC 3122

(57) Claim

1. A process for preparing polyamides, which comprises effecting the polymerization of starting monomers in the presence of at least one triacetonediamine compound of the formula



where R is hydrogen or hydrocarbyl having from 1 to 20 carbon atoms, preferably alkyl having from 1 to 18 carbon atoms, or benzyl.

7. The use of the polyamide of any of claims 3 to 6 for producing filaments, fibres or films.

OPI DATE 10/11/95 APPLN. ID 23442/95  
 AOJP DATE 21/12/95 PCT NUMBER PCT/EP95/01349




AU9523442

(51) Internationale Patentklassifikation 6: <b>C08K 5/3435, C08G 69/48</b>		(11) Internationale Veröffentlichungsnummer: <b>WO 95/28443</b>	
<b>A1</b>		(43) Internationales Veröffentlichungsdatum: <b>26. Oktober 1995 (26.10.95)</b>	
(21) Internationales Aktenzeichen: <b>PCT/EP95/01349</b>		(81) Bestimmungsstaaten: AU, BR, BY, CA, CN, CZ, FI, HU, JP, KR, KZ, MX, NO, NZ, PL, RU, UA, US, europäisches Patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) Internationales Anmeldedatum: <b>12. April 1995 (12.04.95)</b>		<b>Veröffentlicht</b> <i>Mit internationalem Recherchenbericht.</i> <i>Vor Ablauf der für Änderungen der Ansprüche zugelassenen Frist. Veröffentlichung wird wiederholt falls Änderungen eintreffen.</i>	
(30) Prioritätsdaten: P 44 13 177.1      15. April 1994 (15.04.94)      DE P 44 29 089.6      17. August 1994 (17.08.94)      DE			
(71) Anmelder (für alle Bestimmungsstaaten ausser US): <b>BASF AKTIENGESELLSCHAFT [DE/DE]; D-67056 Ludwigshafen (DE).</b>			
(72) Erfinder; und (75) Erfinder/Anmelder (nur für US): <b>WEINERTH, Klaus [DE/DE]; Triftbrunnenweg 49, D-67434 Neustadt (DE). MELL, Karlheinz [DE/DE]; Dackenheim Strasse 2, D-67067 Ludwigshafen (DE). MATTHIES, Paul [DE/DE]; Triftnerstrasse 59, D-69121 Heidelberg (DE). BEER, Ludwig [DE/DE]; Mundenheimer Strasse 160, D-67061 Ludwigshafen (DE).</b>			
(74) Gemeinsamer Vertreter: <b>BASF AKTIENGESELLSCHAFT; D-67056 Ludwigshafen (DE).</b>			

685271

(54) Title: **INHERENTLY LIGHT- AND HEAT-STABILIZED POLYAMIDES**

(56) Bezeichnung: **INHÄRENT LICHT- UND HITZESTABILISIERTE POLYAMIDE**



(I)

(57) Abstract

The invention relates to a process for the production of inherently light- and heat-stabilized polyamides, in which polymerisation and polycondensation take place in the presence of at least one tri-acetone diamine compound of formula (I), wherein R is hydrogen or hydrocarbon groups with 1-20 carbon atoms, preferably alkyl groups with 1-18 carbon atoms, or a benzyl group.

(57) Zusammenfassung

Die Erfindung betrifft ein Verfahren zur Herstellung von inhärent licht- und hitzestabilisierten Polyamiden, wobei die Polymerisation bzw. Polykondensation in Gegenwart von mindestens einer Triacetondiamin-Verbindung der Formel (I) durchgeführt wird, wobei R Wasserstoff oder Kohlenwasserstoffreste mit 1 bis 20 C-Atomen, bevorzugt Alkylgruppen mit 1 bis 18 C-Atomen, oder eine Benzylgruppe bedeutet.

- 1 -

Inherently light- and heat-stabilized polyamides

The present invention relates to improved polyamides. More particularly, the present invention relates to inherently light- and heat-stabilized polyamides. The present invention further relates to a process for preparing these polyamides and to their use.

The heat stability of polyamides, including nylon 6 and nylon 66, is insufficient for some applications. For instance, coloration problems can arise as a result of chemical changes (oxidative/thermal damage) to the polymer during carpet yarn or textile fabric heat setting. Both continuous filaments and staple fibers may be affected. It is known to add stabilizers to the polyamide to improve these properties. Such an addition can take place before, during or after the polymerization, for example during the processing. The customary known stabilizers are mixed into the polymer and are not bonded to the polymer chain. During processing or use they can migrate, evaporate or wash out of the polymer more or less readily, so that the effectiveness of the stabilization decreases in an undesirable manner and the surroundings (air, dyebath) may become contaminated.

DE-A-20 40 975, Sankyo Co. Ltd., describes the stabilization of synthetic polymers, including polyamides, with 4-aminopiperidine derivatives. Among the multiplicity of 4-aminopiperidine derivatives disclosed therein is 4-amino-2,2,6,6-tetramethylpiperidine (cf. No. 32 on page 8 of the document). However, this piperidine derivative is neither particularly singled out nor used in any Example. According to this reference, the 4-aminopiperidine derivatives are mixed with the ready-prepared polymer without becoming attached to the polymer chain.

DE-C-39 32 912, Sandoz, concerns polyamides containing radicals with sterically hindered amino groups,

- 2 -


incorporated in the molecule. The number of radicals is from 5 to 200 per polyamide molecule on average. According to this reference, these polyamides are useful, inter alia, for improving the dyeability of polyamides and as  
5 light stabilizers for plastics; they are to be incorporated in amounts of 1-10% by weight, particularly in the melt.

A paper in Poly. Deg. and Stab. 21, 251-262 (1988), states that the light stability of nylon 66 is improved  
10 on addition of 2,2,6,6-tetramethyl-4-piperidinol (TMP). The authors assume (see p. 259) that the TMP has reacted with the carboxyl end groups of the polyamide during a melt postcondensation of the TMP-including nylon 66 at 275°C under a water vapor atmosphere. But, they say,  
15 there are signs of (undesirable) crosslinking during the later stages of irradiation.

It is known to use amines or mono- and dicarboxylic acids as chain regulators in the polymerization of polyamides, and monocarboxylic acids are very predominantly used for  
20 this purpose in practice.

It is an object of the present invention to provide inherently light- and heat-stabilized polyamides and processes for preparing them.

We have found that this object is achieved when a  
25 triacetonediamine compound of the formula




where R is hydrogen (4-amin-2,2,6,6-tetramethyl-piperidine) or hydrocarbyl having from 1 to 20 carbon atoms, preferably alkyl (4-amino-1-alkyl-2,2,6,6-tetramethylpiperidine) having from 1 to 18 carbon atoms, or


- 3 -

benzyl, is added before or in the course of the polymerization of the polyamides.

The present invention accordingly provides a process for preparing polyamides, which comprises effecting the polymerization of starting monomers in the presence of at least one triacetonediamine compound of the formula



where R is hydrogen or hydrocarbyl having from 1 to 20 carbon atoms, preferably alkyl having from 1 to 18 carbon atoms, or benzyl. Preferred embodiments of the process of this invention are described in subclaims. The present invention further provides an inherently light- and heat-stabilized polyamide containing an amine radical of the formula



where R is as defined above, chemically bonded to the polymer chain. Preferred polyamides of this invention are defined in corresponding subclaims.

The triacetonediamine compound is added to the starting monomers or the polymerizing reaction mixture and becomes bonded to the end of the polymer chain through reaction of its primary amino group with the starting monomers or with the carboxyl groups of the polyamide being formed. The secondary amino group of the triacetonediamine compound does not react because of steric hindrance.

- 4 -

Thus, the triacetonediamine compound also acts as a chain regulator.

The chemical bonding of the triacetonediamine compound to the polymer chain of the polyamide results in inherently stabilized polyamides being obtained. The process of this invention thus offers the advantage of obviating the otherwise necessary separate step of mixing a stabilizer into the polyamide. This eliminates problems or quality reductions as can arise on incorporation of a stabilizer following surface application to the polyamide granules as a result of incompatibility, viscosity degradation, migration, vaporization or washoff of the stabilizer or a twofold stress as with compounding, for example. The use of the triacetonediamine compound in the process of this invention protects the polyamides against damage by the action of heat and thermal oxidation in processing and use.

The polymerization of the starting monomers in the presence of the triacetonediamine compound is preferably carried out according to customary processes. For instance, the polymerization of caprolactam in the presence of triacetonediamine ( $R = H$ ) can be carried out for example according to the continuous processes described in DE 14 95 198 and DE 25 58 480. The polymerization of 66 salt in the presence of triacetonediamine can be carried out by the customary batchwise process (see: Polymerization Processes p. 424-467, especially p. 444-446, Interscience, New York, 1977) or by a continuous process, for example as described in EP 129 196. In principle, the triacetonediamine compound and the starting monomers can be introduced into the reactor separately or as a mixture. The triacetonediamine compound is preferably added according to a predetermined amount/time program.

In a preferred embodiment of the process of this invention, the starting monomers used for polymerization

- 5 -

ar caprolactam and at least one dicarboxylic acid A selected from adipic acid, sebacic acid and terephthalic acid and at least one diamine selected from hexamethylenediamine and tetramethylenediamine, or dicarboxylic acid-diamine salts thereof. Caprolactam is particularly preferred. Dicarboxylic acid A is particularly preferably adipic acid or terephthalic acid. Given the appropriate choice of starting monomers, the polymerization will lead to the preferred polyamides nylon 6, nylon 66, nylon 46 or nylon 610.

In a preferred embodiment, the triacetonediamine compound is added to the starting monomers in an amount of from 0.03 to 0.8 mol%, preferably from 0.06 to 0.4 mol%, based on 1 mol of carboxamide groups of the polyamide. This statement of quantity relates for example to 1 mole of caprolactam when nylon 6 is to be prepared or to 0.5 mol of 66 salt when nylon 66 is to be prepared. It was found that amounts below 0.03 mol% do not ensure sufficient stabilization, whereas amounts above 0.8 mol% make it impossible to achieve the desired degree of polymerization owing to the regulating effect of the triacetonediamine compound.

In a preferred embodiment of this invention, the triacetonediamine compound is combined with at least one customary chain regulator. Examples of suitable chain regulators are monocarboxylic acids such as acetic acid, propionic acid and benzoic acid. The chain regulator combination and the amounts used are selected inter alia according to the amino end group content desired for the end product and according to the desired melt stability. The amino end group content depends on the dyeability desired for the filaments or fibers. The melt stability depends on the practical requirements of processing products, especially in relation to spinning.

The nylon 6 (polycaprolactam) prepared by the process of this invention, as well as the triacetonediamine com-



- 6 -

pound, preferably contains dicarboxylic acids B as chain regulators. More particularly, such nylon 6 products, as well as possessing the requisite melt stability, the desired filament or fiber dyeability and good light and heat stability, also possess improved strength for the filaments obtained, especially filaments produced by high-speed spinning at very high rates of speed.

The dicarboxylic acids B used as chain regulators in combination with the triacetonediamine compound can be identical to or different from the dicarboxylic acids used as dicarboxylic acid A. They are preferably selected from: C<sub>4</sub>-C<sub>10</sub>-alkanedicarboxylic acids, especially adipic acid, azelaic acid, sebacic acid and dodecanedioic acid; C<sub>5</sub>-C<sub>8</sub>-cycloalkanedicarboxylic acids, especially cyclohexane-1,4-dicarboxylic acid; and also benzene- and naphthalene-dicarboxylic acids, especially isophthalic acid, terephthalic acid and naphthalene-2,6-dicarboxylic acid. The dicarboxylic acids B are preferably used in an amount of from 0.06 to 0.6 mol%, preferably from 0.1 to 0.5 mol%, based on 1 mol of carboxamide groups of the polyamide.

In another preferred embodiment, the polymerization of the process of this invention is carried out in the presence of at least one pigment. Preferred pigments are titanium dioxide or inorganic or organic coloring compounds. The pigments are preferably added in an amount of from 0 to 5 parts by weight, especially from 0.02 to 2 parts by weight, based on 100 parts by weight of polyamide. The pigments can be added to the reactor with the starting materials or separately therefrom. The use of the triacetonediamine compound (also as chain regulator constituent) distinctly improves the light stability of the polymer compared with a polymer comprising only pigment and containing no triacetonediamine.

This invention also relates to the use of inherently light- and heat-stabilized polyamide of this invention

- 7 -

for producing filaments, fibers and films. This invention further relates to a process for producing filaments based on polycaprolactam by high-speed spinning at takeoff speeds of at least 4000 m/min and to the filaments thus obtained. In addition, this invention encompasses the use of filaments obtained according to this invention for producing fibers and fabrics and also the fibers and fabrics obtainable by this use.

The Examples which follow illustrate the invention.

10 General remarks concerning the Examples

The relative viscosity of the polyamides (pellets and filaments) was determined in 1% strength solution (1 g/100 ml) in concentrated sulfuric acid (96% by weight) at 25°C. The end group content was determined by acidimetric titration. The amino end groups were titrated with perchloroacetic acid in a solution in 70:30 (parts by weight) phenol/methanol. The carboxyl end groups were titrated with potassium hydroxide solution in a solution in benzyl alcohol.

20 The level in the polyamides of the triacetonediamine compound and of any dicarboxylic acids can be determined by hydrolyzing a sample in dilute mineral acid and analyzing the hydrolyzate by customary methods, for example by gas chromatography.

25 The heat stability of the polyamide filaments was determined under conditions which substantially correspond to those of heat setting processes in subsequent treatment stages, for example heat setting of BCF (bulked continuous filament) or tenter setting of textile fabrics.

30 5 g bunks of the drawn filaments were rapidly introduced on a holder together with the comparative samples into a through-circulation oven preheated to 185°C and left therein for 120 seconds from reattainment of the air temperature measured in direct sample vicinity. The

- 8 -

sample was then immediately removed and cooled down in air at 20°C room temperature. Filaments to be compared were treated together.

5 The damage incurred (compared with an untreated sample of the same filament) was determined through the decrease in the relative viscosity and the amino group content and the increase in the carboxyl group content.

10 The absolute decrease in the basic groups is then converted into a percentage decrease, based on the untreated yarn sample, to arrive at a more useful figure for actual service.

15 The ultimate extension was determined using an Uster Tensorapid I and a clamped length of 200 mm in the case of partially oriented yarn (POY), of 500 mm in the case of drawn and textured yarn. The yarn time-to-rupture was within the range 20±2 seconds. The pretensioning force was 0.025 cN/dtex in the case of POY and 0.05 cN/dtex in the case of drawn yarn.

20 The tenacity  $R_E$  was calculated according to the following equation:

$$R_E = F_E / Tt_v$$

where  $F_E$  is the ultimate tensile strength [cN] and  $Tt_v$  is the original linear density [dtex]. The ultimate tensile strength value used was the largest value obtained in the  
25 ultimate extension measurements.

The ultimate extension  $E_E$  was determined as the ratio of the length change  $\Delta l$  at the moment of attainment of the ultimate tensile strength to the original length  $l_v$  of the sample according to the following equation:

30 
$$E_E = \Delta l \cdot 100\% / l_v$$

where  $\Delta l$  is the difference in the length of the sample at the time of application of the ultimate tensile strength,  $l_E$ , and the original length  $l_v$ .

- 9 -

## R presentativ Example 1

Th polym rization r actor used was a VK tub vertical column reactor as described in EP 20946 composed of stainless steel, material No. 1.4541. The VK tube had an operating capacity of 340 l and was heated with a heat transfer oil.

A mixture of 100 parts by weight of molten caprolactam, 0.5 part by weight of water and 0.33 part by weight of terephthalic acid was continuously introduced into the first reaction zone at the top of the VK tube at a rate of 41 kg/h with stirring. At the same time, triacetone-diamine was continuously fed as a separate stream into the first reaction zone of the VK tube at a rate of 55 ml/h. The concentration of triacetonediamine was accordingly 0.087 mol%, and that of terephthalic acid 0.23 mol%, each based on 1 mol of caprolactam. The temperature of the first reaction zone was 266°C; the pressure in the vapor phase above the first reaction zone was 1.5 bar absolute. The polycaprolactam was discharged from the VK tube at the base thereof, converted into pellets, extracted with hot water and dried. The dried polymer had a relative viscosity of 2.70, an amino end group content of 39 meq/kg and a carboxyl end group content of 65 meq/kg.

The product was spun at high speed as godet POY from jets having a hole diameter of 0.2 mm and a capillary length of 0.6 mm on an Ems-Inventa pilot spinning plant at a melt temperature of 275°C and a rate of 23 g/min per jet.

The speeds were 4520 m/min for the 1st duo, 4530 m/min for th 2nd duo and 4500 m/min for the Barmag Craft winder.

Below the jet the yarn was cooled in a Barmag transv rse flow quench box using a 20°C/65% relative humidity air stream having a velocity f 0.4 m/sec. Th yarn was spin

- 10 -

finish d with a comm rcial spin finish composition (Limanol E 100, from Schill & Silacher, 0.65% yarn add-on) in the quench box via a metering pump and ceramic oilers. The POY had the following properties: ultimate  
5 extension 72%, tenacity 4.1 cN/dtex, Uster standard test  $U\% = 0.6$ .

The yarn was then cold-drawn at 820 m/min on a Zinser 14 S draw-twist machine to a draw ratio of 1:1.363. The  
10 yarn thus obtained had an ultimate extension of 37%, a tenacity of 5.2 cN/dtex and an Uster uniformity  $U\%$  (standard test) of 0.7. The 12 filament linear density was 43.1 dtex.

The relative viscosity was 2.70, the amino end group  
15 concentration was 35 and the carboxyl end group concentration was 63 meq/kg.

#### Comparative Example 1

Commercial nylon 6 of relative viscosity 2.67 without triacetonediamine was spun under identical conditions as  
20 in Representative Example 1. The POY had the following properties: ultimate extension 73%, tenacity 4.0 cN/dtex, Uster standard test  $U\% = 0.6$ .

The yarn was then cold-drawn to a draw ratio of 1:1.336. The yarn thus obtained had an ultimate extension of 43%,  
25 a tenacity of 4.8 cN/dtex and an Uster uniformity  $U\%$  (standard test) of 0.5. The linear density of the 12 filament yarn was 43.8 dtex. The relative viscosity was 2.66, the amino end group content was 32 meq/kg, and the carboxyl end group content was 53 meq/kg.

The yarn was subjected to a 120 s heat treatment in hot  
30 air at 185°C and showed the following values:

- 11 -

Tabl 1

		Representative Example 1	Comparative Example 1
5	Relative viscosity untreated	2.70	2.66
	treated	2.45	2.20
	decrease	-0.25	-0.46
	Amino end groups untreated	35	32
	(meq/kg) treated	26	21
	decrease	-9	-11
	decrease (%)	-26%	-34%
	Carboxyl end groups untreated	63	53
	(meq/kg) treated	67	71
	increase	+4	+18

Table 1 reveals that the nylons 6 of this invention decrease less in relative viscosity and amino group content and increase less in carboxyl group content in the heat treatment than the polyamide of Comparative Example 1 and thus possess better heat stabilization.

#### Representative Example 2

Caprolactam was polymerized in the same VK tube as in Representative Example 1 in the presence of 0.38 mol% of terephthalic acid, 0.20 mol% of triacetonediamine, 0.5% by weight of water and 0.3% by weight of titanium dioxide (as delusterant). The polymerization was carried out in the first reaction zone at a temperature of 255°C and at atmospheric pressure with a throughput of 25 kg/h. The procedure was otherwise in correspondence with that described in Representative Example 1. The dried product had a relative viscosity of 2.37, an amino end group content of 45 meq/kg and a carboxyl end group content of 79 meq/kg.

The product was melted in a Barmag single-screw extruder and fed at a melt temperature of 270°C into a Barmag SP 42 spinning system. The melt was spun at a rate of 22.6 g/min per jet through 12-hole spinning jets having

- 12 -

capillary holes 0.20 mm in diameter and 0.60 mm in length to produce 12 filament strands having an as-spun (POY) linear density of 52 dtex and taken up at 4500 m/min. After passing through a quench box with a transverse quench flow of 0.40 m/sec and spin finishing with from 0.60 to 0.65% of a commercial spin finish composition (Limanol E 100 from Schill & Seilacher as 8% strength solution) the filament strands were taken off via 2 godet duos at 4510 m/min and 4535 m/min, respectively. The winding head used was an axially driven Barmag Craft winder. The POY had an ultimate extension of 65%, a tenacity of 4.6 cN/dtex and a boil-off shrinkage of 9%.

The POY was cold-drawtwisted at 748 m/min on a Rieter J5/10a draw-twist machine. The yarn tension in the prestretch zone was 0.8%, and the total draw ratio was 1:1.298.

The drawn filament yarns had an ultimate extension of 36%, a tenacity of 5.2 cN/dtex, a linear density of 44 dtex for 12 filaments and an Uster U % (standard test) of 0.7.

The relative viscosity was found to be 2.41, the amino end group content was found to be 42 meq/kg and the carboxyl end group content was found to be 74 meq/kg.

#### Comparative Example 2

Commercial nylon 6 having a relative viscosity of 2.39 and containing no triacetonediamine was extruded in the manner described in Representative Example 2. Cooling and spin finishing of the yarn were carried out as described above. The POY was wound up at 4500 m/min without godets. The POY had an ultimate extension of 62%, a tenacity of 4.2 cN/dtex and a boil-off shrinkage of 9%.

The POY was cold-drawn as in Representative Example 2 to a total draw ratio of 1:1.279. The drawn filament yarn

- 13 -

had an ultimate extension of 34%, a tenacity of 4.6 cN/dtex, a linear density of 43.6 dtex for 12 filaments and an Uster valu U % (standard test) of 0.9.

5 The relative viscosity of the yarn was 2.41, the amino end group content was 25 meq/kg and the carboxyl end group content was 65 meq/kg.

The yarn was subjected to conditions corresponding to a textile tenter setting (185°C hot air, 120 sec) and the following properties were measured:

10 Table 2

		Representative Example 2	Comparative Example 2
Relative viscosity	untreated	2.41	2.41
	treated	2.28	1.84
	decrease	-0.13	-0.57
Amino end groups (meq/kg)	untreated	42	25
	treated	34	13
	decrease	-8	-12
	decrease (%)	-19%	-48%
15 Carboxyl end groups (meq/kg)	untreated	74	65
	treated	75	93
	increase	+1	+28

Table 2 clearly shows that caprolactam polymerized to nylon 6 in the presence of triacetonediamine has better heat stabilization than the nylon 6 of Comparative Example 2, which contains no triacetonediamine.

## 20 Representative Example 3

Polyamide prepared as in Representative Example 2 but without the addition of titanium dioxide was subjected to high-speed spinning in accordance with Representative Example 2. The POY had an ultimate extension of 64%, a  
25 tenacity of 4.7 cN/dtex and a boil-off shrinkage of 10%.



- 14 -

The drawing was carried out under the conditions recited in Representative Example 2. Thereafter the drawn yarn had an ultimate extension of 37%, a tenacity of 5.4 cN/dtex, a boil-off shrinkage of 14%, an Uster  
 5 uniformity U % (standard test) of 0.8 and a 12-filament linear density of 44 dtex.

The relative viscosity was 2.40, the amino end group content was 42 meq/kg, and the carboxyl end group content was 74 meq/kg.

#### 10 Comparative Example 3A/3B

2 types of commercial nylon 6 of relative viscosity 2.40 (3A) and 2.44 (3B), respectively, were subjected to high-speed spinning in accordance with Representative Example 2. The spinning temperature was 275°C, and the  
 15 speed of the godet duos was 4510 m/min and 4520 m/min, respectively.

Table 3

The POY had the following properties:

	<u>Representative Example 3A</u>	<u>Representative Example 3B</u>
20 Ultimate extension	64%	68%
Tenacity	4.4 cN/dtex	4.2 cN/dtex
Boil-off shrinkage	8%	8%
Uster (standard test) U%	0.6%	0.5%
12-filament linear density	51 dtex	52 dtex
The POY was then cold-drawn on draw-twist machines to the draw ratios:		
	1:1.257	1:1.313
25 and had the data:		
Ultimate extension	44%	38%
Tenacity	5.0 cN/dtex	4.8 cN/dtex
Boil-off shrinkage	11%	12%
Uster (standard test) U%	0.6%	0.8%
30 12-filament linear density	45 dtex	43 dtex

- 15 -

The following data were determined following the heat-air treatment:

		Rep. Ex. 3	Comp. Ex. 3A	Comp. Ex. 3B
Relative viscosity	untreated	2.40	2.37	2.45
	treated	2.19	1.93	2.23
	decrease	-0.21	-0.44	-0.22
Amino end groups (meq/kg)	untreated	42	24	43
	treated	34	16	27
	decrease	-8	-8	-16
	decrease (%)	-19%	-33%	-37%
Carboxyl end groups (meq/kg)	untreated	74	65	51
	treated	78	86	64
	increase	+4	+21	+13

According to Table 3, nylon 6 of this invention has better heat stabilization than the nylon 6 types of the comparative examples.

#### Representative Example 4

Caprolactam was polymerized in the same VK tube as in Representative Example 1 in the presence of 0.55% by weight (0.375 mol%) of terephthalic acid, 0.33% by weight (0.239 mol%) of triacetonediamine, 0.5% by weight of water and 0.3% by weight of titanium dioxide. The polymerization was carried out in the first reaction zone at a temperature of 255°C and at atmospheric pressure with a throughput of 25 kg/h. The procedure was otherwise in correspondence with that described in Representative Example 1. The dried product had a relative viscosity of 2.42, an amino end group content of 46 meq/kg and a carboxyl end group content of 70 meq/kg. The extractables content was 0.38%.

This was followed by godetless spinning at 4500 m/min in accordance with Comparative Example 2, then cold-drawing to a draw ratio of 1:1.229 and warping at 600 m/min.

The POY had a 12 filament linear density of 52 dtex, an ultimate extension of 59% and a tenacity of 4.1 cN/dtex.

- 16 -

An average of 0.5 defects/100 km were found in the Elkometer test (gap siz 45  $\mu$ m).

The drawn yarn has an ultimate extension of 36% and a tenacity of 4.3 cN/dtex. The 12 filament linear density  
5 was 46 dtex.

#### Comparative Example 4

Caprolactam was polymerized in the same VK tube as in Representative Example 4 in the presence of 0.53% by weight (0.361 mol%) of terephthalic acid, 0.5% by weight  
10 of water and 0.3% by weight of titanium dioxide. The polymerization was carried out in the first reaction zone at a temperature of 252°C. The procedure was otherwise in correspondence with that described in Representative  
15 Example 4. The dried product had a relative viscosity of 2.39, an amino end group content of 27 meq/kg and a carboxyl end group content of 92 meq/kg. The extractables content was 0.32%.

50 kg of the above nylon 6 chips were admixed with 165 g of triacetonediamine (TAD) (0.33% by weight) in liquid  
20 form by drumming on in a gyro wheel mixer for 2 hours.

The chips accordingly comprised the same amount of TAD in admixture and contained virtually the same terephthalic acid content (as part of the polymer) as the above-described product 4; the two products were identical  
25 except for the manner of the addition of the TAD.

The drummed-on TAD does not absorb completely into the chips. They remain TAD-moist and have a strong amine odor. This property is extremely disadvantageous in handling; in addition, extensive safety precautions are  
30 necessary, since TAD is corrosive.

During the residence time in the spinning system, the viscosity increases normally in the case of Representa-

- 17 -

tive Example 4, whereas it decreases dramatically in the case of Comparative Example 4. Other advantages of Representative Example 4 are the comparatively small change in the number of amino groups and in the extractables content (determination: 16 hours of extraction with methanol under reflux) and the fact that there is significantly less fuming in the spinneret region during spinning.

Table 4

## 10 Chemical data of free-fall yarn

	Rep. Ex. 4		Comp. Ex. 4	
Relative viscosity	2.48 (+ 0.06) <sup>1</sup>		2.24 (-0.15) <sup>1</sup>	
End groups				
Amino (meg/kg)	43	(-3)	54	(+27)
Carboxyl (meg/kg)	67	(-3)	88	(-4)
Extract (%)	1.4	(+1.0)	1.8	(+ 1.5)

1) Values in brackets: change compared with chips used; in the case of Comparative Example 4, compared with the base polymer without TAD.

The spinning and further processing were carried out under the conditions recited in Representative Example 4. The POY had a 12 filament linear density of 52 dtex, an ultimate extension of 54% and a tenacity of 3.8 cN/dtex. An average of 7.5 defects (nodules, broken filaments, loops)/100 km were found in the Elkometer test.

After drawing, the ultimate extension was 35% and the tenacity 4.2 cN/dtex.

- 18 -

Tabl 5

5

	Rep. Ex. 4	Comp. Ex. 4
Spinning breakages 100 kg	1.2	4.0
Elkometer test defects/100 km	0.5	7.5
Drawing defects/100 kg	1.8	14.5
Warping defects/100 km	0.037	> 0.65

As is discernible from Table 5, the nylon 6 of Representative Example 4 according to the invention has lower defect numbers in all processing stages than the nylon 6 of Comparative Example 4, into which the TAD was incorporated by mixing into the polyamide.

In Representative Example 4, TAD is more completely/strongly attached in the polyamide than in Comparative Example 4. Thus, less amine passes into the aqueous phase in extraction processes (in dyeings, for example).

Following one hour extraction with boiling water under reflux of POY wound up without spin finish, the following chemical data were determined:

Table 6

	Rep. Ex. 4	Comp. Ex. 4
Rel. viscosity before extraction	2.42	2.20
after extraction	2.49	2.26
difference	+0.07	+0.06
Amino end groups (mg/kg) before extraction	42	55
after extraction	42	50
diff rance	±0	-5

As is evident from Table 6, the number of amino end groups before and after extraction remains the same in

- 19 -

th polyamide of this invention, whereas the comparative example has fewer amino end groups after extraction. Thus, less amine passes into the aqueous phase on extraction of the polyamide of this invention.

#### 5 Comparative Example 5

Commercial nylon 6 of relative viscosity 2.39, delustered with 0.3% titanium dioxide and containing no triacetone-diamine was spun into filaments in the manner described in Comparative Example 2.

10 The POY had a 12 filament linear density of 51 dtex, an ultimate extension of 57% and a tenacity of 3.8 cN/dtex. After cold drawing to a draw ratio of 1:1.244, the values listed below in Table 7 for the untreated sample were determined.

15 The irradiation and the measurement of the ultimate extension and ultimate tensile strength were carried out jointly with Representative Example 5. The results are listed in Table 7.

#### Representative Example 5

20 Caprolactam was polymerized from the same starting materials and quantities under the conditions specified in Representative Example 4 using the same titanium dioxide type as in Comparative Example 5. The dried polyamide had a relative viscosity of 2.43, an amino end  
25 group content of 44 meq/kg and a carboxyl end group content of 71 meq/kg. The extractables content was 0.36%.

Spinning was carried out godetlessly at 4500 m/min as described in Comparative Example 2. The POY had a 12 filament linear density of 51 dtex, an ultimate extension  
30 of 61% and a tenacity of 4.3 cN/dtex.

After cold drawing to a draw ratio of 1:1.244, the values

- 20 -

listed below in Table 7 for the untreated sample were determined.

The yarn was then wound on frames and irradiated for 28 days in a Xenotest 450 from Heraeus, Hanau, and the residual ultimate extension and the residual ultimate tensile strength were determined in accordance with DIN 53834 using a clamped length of 100 mm on a Zwick UPM 1425 tensile tester. The results are listed in Table 7.

Table 7

		Rep. Ex. 5	Comp. Ex. 5
10	Untreated yarn		
	12-filament linear density (dtex)	44	44
	Ultimate extension (%)	35	39
	Ultimate tensile strength (cN)	199	196
	Tenacity (cN/dtex)	4.52	4.45
15	After 28 days' irradiation in Xenotest 450		
	Residual ultimate extension (%)	23	16
	(= % of original value) (%)	(66)	(41)
20	Residual ultimate tensile strength	136	97
	(= % of original value) (%)	(68)	(49)

It is clear from Table 7 that the polyamide prepared in the presence of triacetonediamine and  $\text{TiO}_2$  (Representative Example 5) has a distinctly improved light stability compared with a comparative polymer (Comparative Example 5) including only  $\text{TiO}_2$  and no triacetonediamine.

21

O.Z. 0030/44840

BASF Aktiengesellschaft


October 18, 1996

NAE19930472PCAU G/Nb/an

5 We claim:

1. A process for preparing polyamides, which comprises effecting the polymerization of starting monomers in the presence of at least one triacetonediamine compound of the formula

10




15 where R is hydrogen or hydrocarbyl having from 1 to 20 carbon atoms, preferably alkyl having from 1 to 18 carbon atoms, or benzyl.

2. A process as claimed in claim 1, wherein the polymerization is further carried out in the presence of at least one pigment.

20

3. Inherently light- and heat-stabilized polyamide containing an amine radical of the formula

25



30 where R is as defined in claim 1, chemically bonded to the polymer chain.



22

4. Polyamide as claimed in claim 3, comprising at least one pigment.
5. Polyamide as claimed in claim 3 or 4, obtained, by one of the processes for preparing polyamides claimed in any of claims 1 to 2.
6. Polyamide as claimed in any of claims 3 to 5, containing from 0.03 to 0.8 mol%, preferably 0.06 to 0.4 mol%, of the amine radical, based on 1 mol of carboxamide groups of the polymer chain of the polyamide.
7. The use of the polyamide of any of claims 3 to 6 for producing filaments, fibres or films.
8. A process for producing polyamide filaments as set forth in any of claims 3 to 6 or obtained as claimed in claim 1 or 2 by high-speed spinning at takeoff speeds of at least 4000 m/min.
9. Filaments obtained according to the process as claimed in claim 8.
10. The use of the filaments obtained according to the process as claimed in claim 8 for producing fibres and fabrics.
11. A process as claimed in claim 8 wherein the polyamide filaments are nylon-6 (polycaprolactam).

**DATED** on this 23rd day of September, 1997

**BASF AKTIENGESELLSCHAFT**


WATERMARK PATENT & TRADEMARK ATTORNEYS  
290 BURWOOD ROAD  
HAWTHORN VICTORIA 3122  
AUSTRALIA



# Inherently light- and heat-stabilized polyamides

## Abstract

A process for preparing inherently light- and heat-stabilized polyamides comprises polymerizing in the presence of at least one triacetonediamine compound of the formula



where R is hydrogen or hydrocarbyl having from 1 to 20 carbon atoms, preferably alkyl having from 1 to 18 carbon atoms, or benzyl.

## INTERNATIONAL SEARCH REPORT

Intern. Appl. Application No.

PCT/EP 95/01349

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 C08K5/3435 C08G69/48

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A A	FR,A,2 074 871 (SANKYO) 8 October 1971 & DE,A,20 40 975 (SANKYO) 10 February 1972 cited in the application ---	
A A	EP,A,0 379 470 (SANDOZ) 25 July 1990 & DE,A,39 32 912 (SANDOZ) 11 April 1991 cited in the application ---	
A	PATENT ABSTRACTS OF JAPAN vol. 017, no. 251 (C-1060) 19 May 1993 & JP,A,05 001 223 (SHOWA DENKO KK) 8 January 1993 see abstract ---	
A	DE,A,32 33 951 (HULS) 15 March 1984 ---	
A	DE,A,32 33 953 (HULS) 15 March 1984 ---	
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.**\* Special categories of cited documents :**

- \* "A" document defining the general state of the art which is not considered to be of particular relevance
- \* "E" earlier document but published on or after the international filing date
- \* "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \* "O" document referring to an oral disclosure, use, exhibition or other means
- \* "P" document published prior to the international filing date but later than the priority date claimed

- \* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* "A" document member of the same patent family

Date of the actual completion of the international search

13 September 1995

Date of mailing of the international search report

29.09.1995

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 631 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Leroy, A

## INTERNATIONAL SEARCH REPORT

Intern. Appl. Application No.

PCT/EP 95/01349

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR,A,2 513 646 (SUMITOMO) 1 April 1983 -----	

## INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Appl. Application No.

PCT/EP 95/01349

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2074871	08-10-71	CH-A- 553838	13-09-74
		DE-A- 2040975	10-02-72
		GB-A- 1318559	31-05-73
		NL-A- 7011773	12-07-71
		US-A- 3684765	15-08-72
DE-A-2040975	10-02-72	CH-A- 553838	13-09-74
		FR-A- 2074871	08-10-71
		GB-A- 1318559	31-05-73
		NL-A- 7011773	12-07-71
		US-A- 3684765	15-08-72
EP-A-0379470	25-07-90	DE-A- 3901716	26-07-90
		DE-A- 3901717	26-07-90
		DE-A- 3930089	21-03-91
		EP-A- 0618256	05-10-94
		DE-D- 69007092	07-04-94
		DE-T- 69007092	21-07-94
		WO-A- 9103511	21-03-91
		EP-A- 0461206	18-12-91
		JP-T- 4501881	02-04-92
DE-A-3932912	11-04-91	DE-D- 69007092	07-04-94
		DE-T- 69007092	21-07-94
		WO-A- 9103511	21-03-91
		EP-A- 0461206	18-12-91
		JP-T- 4501881	02-04-92
DE-A-3233951	15-03-84	NONE	
DE-A-3233953	15-03-84	NONE	
FR-A-2513646	01-04-83	JP-C- 1490843	07-04-89
		JP-A- 58057444	05-04-83
		JP-B- 63039014	03-08-88
		DE-A- 3233353	07-04-83
		GB-A- 2107719	05-05-83

## INTERNATIONALER RECHERCHENBERICHT

Internat. Patentamt

PCT/EP 95/01349

A. KLASSIFIZIERUNG DES ANMELDUNGSGEGENSTANDES  
IPK 6 C08K5/3435 C08G69/48

Nach der Internationalen Patentklassifikation (IPK) oder nach der nationalen Klassifikation und der IPK

## B. RECHERCHIERTE GEBIETE

Recherchierte Mindestprüfung (Klassifikationssymbole und Klassifikationssymbole)

IPK 6 C08K C08G

Recherchierte aber nicht zum Mindestprüfung gehörende Veröffentlichungen, soweit diese unter die recherchierten Gebiete fallen

Während der internationalen Recherche konsultierte elektronische Datenbank (Name der Datenbank und evtl. verwendete Suchbegriffe)

## C. ALS WESENTLICH ANGESEHENE UNTERLAGEN

Kategorie	Bezeichnung der Veröffentlichung, soweit erforderlich unter Angabe der in Betracht kommenden Teile	Betr. Anspruch Nr.
A	FR,A,2 074 871 (SANKYO) 8. Oktober 1971	
A	& DE,A,20 40 975 (SANKYO) 10. Februar 1972 in der Anmeldung erwähnt	
A	EP,A,0 379 470 (SANDOZ) 25. Juli 1990	
A	& DE,A,39 32 912 (SANDOZ) 11. April 1991 in der Anmeldung erwähnt	
A	PATENT ABSTRACTS OF JAPAN vol. 017, no. 251 (C-1060) 19. Mai 1993 & JP,A,05 001 223 (SHOWA DENKO KK) 8. Januar 1993 siehe Zusammenfassung	
A	DE,A,32 33 951 (HULS) 15. März 1984	
A	DE,A,32 33 953 (HULS) 15. März 1984	
	-/-	

☒ Weitere Veröffentlichungen und der Fortsetzung von Feld C zu entnehmen☒ Siehe Anhang Patentfamilie

\* Besondere Kategorien von angegebenen Veröffentlichungen :

"A" Veröffentlichung, die den allgemeinen Stand der Technik definiert, aber nicht als besonders bedeutsam anzusehen ist

"E" älteres Dokument, das jedoch erst am oder nach dem internationalen Anmeldedatum veröffentlicht worden ist

"L" Veröffentlichung, die geeignet ist, einen Prioritätsanspruch zweifelsfrei erscheinen zu lassen, oder durch die das Veröffentlichungsdatum einer anderen im Recherchenbericht genannten Veröffentlichung belegt werden soll oder die aus einem anderen besonderen Grund angegeben ist (wie angegeben)

"O" Veröffentlichung, die sich auf eine mündliche Offenbarung, eine Besetzung, eine Ausstellung oder andere Maßnahmen bezieht

"P" Veröffentlichung, die vor dem internationalen Anmeldedatum, aber nach dem beanspruchten Prioritätsdatum veröffentlicht worden ist

"T" Spätere Veröffentlichung, die nach dem internationalen Anmeldedatum oder dem Prioritätsdatum veröffentlicht worden ist und mit der Anmeldung nicht kollidiert, sondern nur zum Verständnis der Erfindung zugrundeliegenden Prinzipien oder der ihr zugrundeliegenden Theorie angegeben ist

"X" Veröffentlichung von besonderer Bedeutung, die beanspruchte Erfindung kann allein aufgrund dieser Veröffentlichung nicht als neu oder auf erfinderischer Tätigkeit beruhend betrachtet werden

"Y" Veröffentlichung von besonderer Bedeutung, die beanspruchte Erfindung kann nicht als auf erfinderischer Tätigkeit beruhend betrachtet werden, wenn die Veröffentlichung mit einer oder mehreren anderen Veröffentlichungen dieser Kategorie in Verbindung gebracht wird und diese Verbindung für einen Fachmann naheliegend ist

"A" Veröffentlichung, die Mitglied derselben Patentfamilie ist

Datum des Abschusses der internationalen Recherche

13. September 1995

Abschlußdatum des internationalen Recherchenberichts

29. 09 95

Name und Postanschrift der internationalen Recherchenbehörde

Europäisches Patentamt, P.B. 5118 Patentaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tlx. 31 651 epo nl,  
Fax: (+ 31-70) 340-3016

Bevollmächtigter Beauftragter

Leroy, A

## INTERNATIONALER RECHERCHENBERICHT

Intern. wies Alternativen

PCT/EP 95/01349

C (Fortsetzung) ALS WESENTLICH ANGESEHENE UNTERLAGEN

Kategorie	Bezeichnung der Veröffentlichung, soweit erforderlich unter Angabe der in Betracht kommenden Teile	Betr. Anspruch Nr.
A	FR,A,2 513 646 (SUMITOMO) 1. April 1983 -----	